


TRAFFIC

T22882 150 C0600

T491

 Warp
 Weft
 Customs Tariff nr 59032090

Composition of fabric

Number of ends (warp)	.	44 DR/CM
Number of picks (weft)	.	27 DR/CM
Usable width	.	147,0 CM
Full width	Full width	152,0 CM
Weight	ISO3801 1977	190 G/M ²

Corporate Identity

Shrinkage wash 40°C warp	ISO 5077 2007	-3 %
Shrinkage wash 40°C weft	ISO 5077 2007	-3 %
Shrinkage at pressing warp	DIN53894-2 1979	-2,50 %
Shrinkage at pressing weft	DIN53894-2 1979	-2,50 %
Tensile strength warp	ISO13934-1 2013	1940 N
Tensile strength weft	ISO13934-1 2013	1260 N
Tear resistance Elmendorf warp	ISO13937-1 2000	35 N
Tear resistance Elmendorf weft	ISO13937-1 2000	35 N
Seam slippage warp 80 N	ISO13936-2 2004	2,0 MM
Seam slippage warp 120 N	ISO13936-2 2004	4,0 MM
Seam slippage weft 80 N	ISO13936-2 2004	2,0 MM
Seam slippage weft 120 N	ISO13936-2 2004	4,0 MM
Spraytest	ISO 4920 2012	100 ISO 5
Watercolumn	ISO811 1981	500 MM

Colourfastness

		Light	Middle	Dark	Change
Colourfastness to washing 40°C	ISO105C06 2010	5	4/5	4	
Colourfastness to dry cleaning	ISO105X05 1994	5	4/5	4	
Colourfastness to water	ISO105E01 2013	4/5	4	4	
Colourfastness to rubbing dry	ISO105X12 2001	5	4/5	4/5	
Colourfastness to rubbing wet	ISO105X12 2001	4/5	4	4	

Washing symbols


Composition

PA	% Polyamide	100,00 %
----	-------------	----------